

ALPHA[®] ENERGIZED PLUS RA WIRE SOLDER

Type RA per QPL-571-28-89, Passes IPC-TM-650 2.6.3.3

GENERAL DESCRIPTION

ALPHA Energized-Plus is the most effective RA MIL-SPEC rosin core solder yet developed for hand soldering. Similar in design to Energized core solder, Energized-Plus is more active still. It meets the full requirements of QPL listing for Federal Specification **QPL-571-28-89** for Type RA flux-core solder.

FEATURES & BENEFITS

ALPHA Energized-Plus is suitable for use in any electronic hand-soldering application requiring compliance with Military Specifications for RA class fluxes. It is also suitable for those commercial electronic operations modeled after Military Specifications. Some of these include: computer, aerospace, telecommunications, automotive and entertainment industry applications.

The unique activator system of **ALPHA Energized-Plus** enables the flux to penetrate even heavily tarnished surfaces among the following metals:

Beryllium Copper	Lead	Terne (Plate)
Brass	Nickel (Plate)	Tin (Hot Dip)
Bronze	Silver	Tin (Plate)
Cadmium	Solder (Plate)	
Copper	Solder (Hot Dip)	

RESIDUE REMOVAL

In applications requiring cleaning, **ALPHA Energized-Plus** flux residues can be readily removed using either Alpha 564M, 565 or 1003 solvents, an aqueous saponifier cleaning process using Alpha 2110, or semi-aqueous cleaning using Bioact® EC-7.

TECHNICAL DATA

Physical Properties	Typical Values
Softening Point	71°C (160°F)
Rosin Grade	WW per Fed. Spec. LLL-R-626
Water Extract Resistivity	> 50,000 ohm-cm., per QQS-571F
Plasticizer	Very high boiling solvent; creates low smoke and older properties
Wetting Balance Test	Fastest recorded wetting time of all RA MIL-SPEC core solders
QPL Listing Number	571-27-89
J-STD-004	ROM1
ISO 12224	1.1.2

(Continued on Next Page)

SM #1079 2014-10-28

an Alent plc Company

ALPHA Global Headquarters
300 Atrium Drive, Somerset, NJ 08873 USA • 1-800-367-5460 • www.alpha.alent.com

The information contained herein is based on data considered accurate and is offered at no charge. No warranty is expressed or implied regarding the accuracy of this data. Liability is expressly disclaimed for any loss or injury arising out of the use of this information or the use of any materials designated.

ALPHA is a registered trademark of Alpha Metals, Inc.

© 2014 ALPHA

ALPHA[®] ENERGIZED PLUS RA WIRE SOLDER

Type RA per QPL-571-28-89, Passes IPC-TM-650 2.6.3.3

AVAILABILITY

Alloy Description	Flux Loading	Wire
63Sn/37Pb	P2 and P3 (2.2% and 3.3% nominal)	.010" to .125" (Spool Weight 1, 5, 20 Lbs.)
60Sn/40Pb	P2 and P3 (2.2% and 3.3% nominal)	.010" to .125" (Spool Weight 1, 5, 20 Lbs.)
40Sn/60Pb	P2 and P3 (2.2% and 3.3% nominal)	.010" to .125" (Spool Weight 1, 5, 20 Lbs.)
10Sn/88Pb/2Ag	P2 (2.2% nominal)	.010" to .125" (Spool Weight 1, 5, 20 Lbs.)
5Sn/93.5Pb/1.5Ag	P2 (2.2% nominal)	.010" to .125" (Spool Weight 1, 5, 20 Lbs.)
Vaculoy SACX0307 *	P2 and P3 (2.2% and 3.3% nominal)	.010" to .125" (Spool Weight 1, 5, 20 Lbs.)

* Lead-Free Alloy

This material can also be made available in an alloy that is nominally 95% Sn and 5% Sb. Please contact your local CEAM representative to discuss flux, loading, diameter and minimum order quantities for this alloy.

ALPHA Energized-Plus is available in ESD approved plastic spooling per the DOD 2000 specification.

SAFETY

ALPHA Energized-Plus is not considered toxic, however, its use in typical soldering processes will generate a small amount of decomposition and reaction product fumes. These fumes must be adequately exhausted for operator safety and comfort.

SHELF LIFE

If >36 months from manufacture, please submit sample Alpha Metals Inc for testing.