TDS # 1035

CHEMTRONICS® Technical Data Sheet

Flux-Off® Rosin Flux Remover

PRODUCT DESCRIPTION

The Flux-Off[®] Rosin formulation is a fast drying aerosol that quickly and completely removes R, RMA, RA, and synthetic flux residue. With it's low surface tension and superior wetting properties, Flux-Off[®] Rosin removes harmful residues in tight tolerance areas.

- Removes R, RMA, RA, and synthetic flux residues
- Penetrates hard to reach areas
- Evaporates quickly
- Leaves no residue
- Removes oil, grease, ionic and non-ionic residues
- Has low odor
- Non-corrosive formulation
- Contains no CFCs or HCFCs

TYPICAL APPLICATIONS

Flux-Off® Rosin removes flux residues and cleans:

- Chip Carriers
- Heat Sinks
- Plugs
- Printed Circuit Boards
- Relays
- Sockets
- Surface Mount Device Pads
- Switches

TYPICAL PRODUCT DATA AND PHYSICAL PROPERTIES

PROPERTIES					
Boiling Point	141°F Initial				
Solubility in Water	20%				
Specific Gravity	0.70				
Evaporation Rate (butyl acetate=1) >1					
Surface Tension 17.3					
(dynes/cm @21.6°C)					
Flash Point (TCC) -20.0°F					
Kauri-Butanol (KB) Number 50					
VOC* Content:	Aerosol Liquid				
CARB	75% 100%				
SCAQMD	603 g/L 720 g/L				
Federal	75% 100%				
RoHS Compliant	ROHS WEEE				
	Compliant				
Shelflife Aeros	sols 5 years				
Liqui	ds 2 years after opening				

^{*}Volatile Organic Compound (VOC) information is calculated on a weight basis using the VOC definition of California Air Resources Board (CARB) Consumer Product Regulations, South Coast Air Quality Management District (SCAQMD) Rule 102 and the Federal definition published in 40 CFR 51.100(s).

COMPATIBILITY

Flux-Off® Rosin is generally compatible with most materials used in the electronics industry. With any cleaning agent compatibility solvent/component must be determined on a non-critical area prior to use.

Material	Compatibility	
ABS	Good	
Buna-N	Good	
EPDM	Poor	
Graphite	Excellent	
HDPE	Excellent	
Kynar TM	Fair	
LDPE	Fair	
Lexan TM	Fair	
Neoprene	Non-Compatible	
Noryl®	Good	
Nylon TM 66	Excellent	
Cross-Linked PE	Excellent	
Polypropylene	Good	
Polystyrene	Not recommended	
PVC	Good	
Silicone Rubber	Not recommended	
$Teflon^{TM}$	Excellent	
Viton TM	Excellent	

Performance				
Product Required for Rosin Removal				
(mg solvent used to remove 1 mg rosin flux)				
Flux-Off Rosin	101			
Conventional Flux Remover	3673			
Rosin Removal Rate (mg / in ² sec.)				
Flux-Off Rosin	4.0			
Conventional Flux Remover	0.3			

USAGE INSTRUCTIONS

For industrial use only.

Read MSDS carefully prior to use.

Spray 4-6" from surface to clean. Wash parts from top to bottom, allowing the liquid to flush away dirt and dissolved grease. For precise application use attached extension tube. Product is Flammable - Do not use near sources of ignition and energized equipment.

TECHNICAL & APPLICATION ASSISTANCE

ITW Chemtronics[®] provides a technical hotline to answer your technical and application related questions. The toll free number is:

1-800-TECH-401.

ES1035 10 oz. Aerosol

ES1035 10 oz. BrushClean Aerosol ES835B 5 oz. BrushClean Aerosol

ES135 1 gallon Liquid ES535 5 gallon Liquid

ES5535 53 gallon Liquid

ENVIRONMENTAL IMPACT DATA					
HCFC-141b	None	HFC	Aerosol -Yes		
HCFC-225	None	nPB	None		

Hydrochlorofluorocarbons (HCFCs) are regulated under the Montreal Protocol as Class II ozone depleting substances. HCFC-141b is no longer produced in the US under this legislation. HCFC-225 is planned for production phase-out in 2015. Hydrofluorocarbons (HFCs) are not currently regulated.

EPA has listed n-propyl bromide (nPB) as an acceptable alternative to ozone depleting substances in metal, precision, and electronics cleaning under Section 612 of the Clean Air Act.

NOTE: This information is believed to be accurate. It is intended for professional end users having the skills to evaluate and use the data properly. ITW CHEMTRONICS[®] does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.

Chemtronics® and Flux-Off® are registered trademarks of ITW Chemtronics. All rights reserved.

All other trademarks herein are trademarks or registered trademarks of their respective owners.

MANUFACTURED BY:

ITW CHEMTRONICS 8125 COBB CENTER DRIVE KENNESAW, GA 30152

1-770-424-4888 REV. B (06/09)

DISTRIBUTED BY:

All-Spec Industries

www.all-spec.com sales@all-spec.com

PH: 800-537-0351 FX: 800-379-9903