



5 Minute® Epoxy

Description: A rapid-curing, general purpose adhesive/encapsulant.

Intended Use: Bonds metals, fabrics, ceramics, glass, wood, and concrete (in combinations)

Product features: **100% reactive, no solvents**
Good solvent resistance
Bonds metals, fabrics, glass, wood, and concrete

Limitations: None

Typical Physical Properties: *Technical data should be considered representative or typical only and should not be used for specification purposes.*

Cured 7 days @ 75°F

| | |
|--|------------------------------------|
| T-peel | 2-3 pli |
| Impact Resistance | 5.5 ft.lb./in.(2) |
| Tensile Elongation | 1% |
| Shore Hardness | 85 Shore D |
| Gap-Fill | Good |
| Dielectric Strength | 490 volts/mils |
| % Solids by Volume | 100 |
| Adhesive Tensile Lap Shear[GBS] | 1,900 psi @ 0.005" bondline |
| Specific Volume | 25.1 in.[3]/lb. |

Uncured

| | |
|----------------------------|-----------------------------------|
| Color | Light Amber |
| Mixed Viscosity | 10,000 cps |
| Mix Ratio by Volume | 1:1 |
| Mix Ratio by Weight | 1:1 |
| Mixed Density | 9.17 lbs./gal.: 1.10 gm/cc |
| Working Time | 3-6 min. (28 gm @ 72°F) |
| Fixture Time | 10-15 min. @ 72°F |
| Functional Cure | 3/4 - 1 hr. @ 72°F |
| Full Cure | 12 |
| Service Temperature | Dry, -40°F to 200°F |

TESTS CONDUCTED

Adhesive Tensile Shear ASTM D 1002
Dielectric Strength, volts/mil ASTM D 149
Cured Hardness Shore D ASTM D 2240
Cured Density ASTM D 792

Surface Preparation: Clean surface by solvent-wiping any deposits of heavy grease, oil, dirt, or other contaminants. Surface can also be cleaned with industrial cleaning equipment such as vapor phase degreasers or hot aqueous baths. If working with metal, abrade or roughen the surface to significantly increase the microscopic bond area and increase the bond strength.

Mixing Instructions: ---- Proper homogenous mixing of resin and hardener is essential for the curing and development of stated strengths. ----

25 ML DEV-TUBE

1. Squeeze material into a small container the size of an ashtray.
2. Using mixing stick included on Dev-tube handle, vigorously mix components for one (1) minute.
3. Immediately apply to substrate.

50 ML/400ML/490 ML CARTRIDGES

1. Attach cartridge to Mark 5 dispensing system.
2. Open tip.
3. Burp cartridge by squeezing out some material until both sides are uniform (ensures no air bubbles are present during mixing).
4. Attach mix nozzle to end of cartridge.
5. Apply to substrate.

Application Instructions:

1. Apply mixed epoxy directly to one surface in an even film or as a bead.
2. Assemble with mating part within recommended working time.
3. Apply firm pressure between mating parts to minimize any gap and ensure good contact (a small fillet of epoxy should

flow out the edges to display adequate gap fill.)

For very large gaps:

1. Apply epoxy to both surfaces
2. Spread to cover entire area OR make a bead pattern to allow flow throughout the joint

Let bonded assemblies stand for recommended functional cure time prior to handling.

CAPABILITIES:

Can withstand processing forces
Do not drop, shock load, or heavily load

Storage: Store in a cool, dry place.

Compliances: None

Chemical Resistance: *Chemical resistance is calculated with a 7 day, room temp. cure (30 days immersion) @ 75F)*

| | | | |
|---------------------|-----------|----------------------|-----------|
| Acetic (Dilute) 10% | Poor | Hydrochloric 10% | Poor |
| Acetone | Poor | Isopropanol | Poor |
| Ammonia | Poor | Kerosene | Excellent |
| Corn Oil | Excellent | Methyl Ethyl Ketone | Poor |
| Cutting Oil | Excellent | Mineral Spirits | Excellent |
| Ethanol | Poor | Motor Oil | Excellent |
| Gasoline (Unleaded) | Excellent | Sodium Hydroxide 10% | Poor |
| Glycols/Antifreeze | Fair | Sulfuric 10% | Poor |

Precautions: Please refer to the appropriate material safety data sheet (MSDS) prior to using this product.

For technical assistance, please call 1-800-933-8266

FOR INDUSTRIAL USE ONLY

Warranty: Devcon will replace any material found to be defective. Because the storage, handling and application of this material is beyond our control, we can accept no liability for the results obtained.

Disclaimer: All information on this data sheet is based on laboratory testing and is not intended for design purposes. ITW Devcon makes no representations or warranties of any kind concerning this data.

Order Information:

| | |
|-------|------------------|
| 14210 | 2.5 oz. |
| 14630 | 9 lb. |
| DA051 | 400 ml cartridge |
| 14250 | 25 ml DevTube |
| 14200 | 15 oz. |
| 14270 | 50 ml Dev-Pak |
| 14098 | 14cc syringe |

Distributed by:

All-Spec Industries 800-537-0351 (phone)
Wilmington, NC 800-379-9903 (fax)
www.all-spec.com sales@all-spec.com