

■ ULTRA ONE®

NATURAL
LATEX
NON-STERILE
AMBIDEXTROUS
TEXTURED FINGERS
EXTENDED BEADED CUFF
FOR SINGLE USE ONLY

POWDER-FREE EXTENDED CUFF EXAMINATION GLOVES

Ultra One® gloves are ideal if high-risk conditions require extended protection for your wrist and forearm. Strong, durable and comfortable, these latex gloves minimize risk through superior barrier protection.

- Extended coverage for wrist and forearm
- Strong and durable for high-risk environments
- Meets or exceeds the emergency medical glove requirements of NFPA 1999, Standard on Protective Clothing for Emergency Medical operations, 2013 edition





| PRODUCT CODE | | | | |
|--------------|-----------|--|--|--|
| S | UL-315-S | | | |
| М | UL-315-M | | | |
| L | UL-315-L | | | |
| XL | UL-315-XL | | | |

| PACKAGING | | | |
|-----------|------------|--|--|
| 50 | Gloves/Box | | |
| 10 | Boxes/Case | | |
| | | | |

| GLOVE PROFILE | | ASTM D 3578 | ULTRA ONE® |
|-----------------------|-----------------------------|----------------------|-------------|
| Length | mm (inches) | min. 220 (8.7) | 300 (11.8) |
| Cuff Thickness | mm (mils) | n/a | 0.17 (6.7) |
| Palm Thickness | mm (mils) | min. 0.08 (3.1) | 0.25 (9.8) |
| Finger Thickness | mm (mils) | min. 0.08 (3.1) | 0.30 (11.8) |
| Tensile Strength | Before Aging After Aging | min. 18 min. 14 | 33 25 |
| Elasticity/Elongation | Before Aging After Aging | min. 650 min. 500 | 750 600 |
| Pinhole Defect Rate* | (AQL) | max. 2.5 | 1.5 |

^{*} Pinhole Defect Rate is FDA minimum requirement.









Caution: This product contains natural rubber latex (latex) which may cause allergic reations in some users. Safe use of this glove by or on latex sensitized individuals has not been established.

