



ELASTOSIL® RT 774

RTV-2 SILICONE RUBBER

Product description

ELASTOSIL® RT 774 is a non-slump, room temperature vulcanizing, condensation-curing, two-component silicone rubber with good primerless adhesion.

Special features

- thixotropic
- non-slump
- medium hardness
- primerless adhesion on glass, aluminium, stainless steel, epoxy powder coatings
- temperature stability: -40 °C to +180 °C; when cured with Catalyst T 78 black: -40 °C to +200 °C

Application

- adhesive for the Appliance industry
- general purpose sealant

Processing

ELASTOSIL® RT 774 is processed in combination with WACKER[®] Catalyst T 77 or WACKER[®] Catalyst T 78. The curing time can be easily adjusted to the particular needs by varying the ratio of component A and B.

We recommend running preliminary tests to optimize conditions for the particular application.

Comprehensive processing instructions are given in our leaflet "Wacker RTV-2 Silicone Rubber - Processing".

Storage

Further information for storage: Store in a dry and cool place. The 'Best use before end' date of each batch is shown on the product label.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety notes

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site http://www.wacker.com.





Product data

Curing of ELASTOSIL® RT 774 with Catalyst T 77 or Catalyst T 78:

Typical general characteristics	Inspection Method	Value
Product data (uncured A, uncured B)		
EL RT 774 (A component)		
Color		white
Viscosity, dynamic at 25 °C (shear rate = 0,5 1/S)	DIN EN ISO 3219	1250000 mPa.s
Viscosity, dynamic at 25 °C (shear rate = 25 1/S)	DIN EN ISO 3219	90000 mPa.s
Viscosity at 23 °C	DIN 53018	-
Density at 23 °C	ISO 1183-1 A	1,32 g/cm ³
Catalyst T 77 (B component)		
Color		black
Viscosity at 23 °C (D = 0.5 1/s)	DIN 51562	-
Viscosity at 23 °C (D = 25 1/s)	DIN 51562	-
Viscosity at 23 °C	DIN 53018	150000 mPa s
Density at 23 °C		1,1 g/cm ³
Catalyst T 78 (B component)		
Color		black
Viscosity at 23 °C (D = 0.5 1/s)	DIN 51562	-
Viscosity at 23 °C (D = 25 1/s)	DIN 51562	-
Viscosity at 23 °C	DIN 53018	350000 mPa s
Density at 23 °C		1,1 g/cm ³
Product data (mix of A+B)		
EL RT 774 / T 77		
Pot life	10 : 1	15 - 20 min
Curing time, 10 : 1		45 - 60 min
EL RT 774 / T 78		
Pot life	10 : 1	5 - 10 min
Curing time, 10 : 1		15 - 30 min
Product data (cured with T 77)		
Color		anthracite
Density at 23 °C in water	DIN EN ISO 1183-1	1,37 g/cm ³
Hardness Shore A	DIN 53 505 / ISO 868	38
Tensile strength	DIN 53504 S1 / ISO 37	2,1 N/mm ²
Elongation at break	DIN 53504 S1 / ISO 37	300 %
Tear strength		6,2 N/mm
Product data (cured with T 78)		
Color		anthracite
Density at 23 °C in water	DIN EN ISO 1183-1	1,37 g/cm ³
Hardness Shore A	DIN 53 505 / ISO 868	42
Tensile strength	DIN 53504 S1 / ISO 37	' 2,1 N/mm ²
Elongation at break	DIN 53504 S1 / ISO 37	300 %
Tear strength		7,0 N/mm

These figures are only intended as a guide and should not be used in preparing specifications.





The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.

The management system has been certified according to DIN EN ISO 9001 and DIN EN ISO 14001

WACKER® is a trademark of

Wacker Chemie AG. ELASTOSIL® is a trademark of Wacker Chemie AG. For technical, quality, or product safety questions, please contact:

Wacker Chemie AG Hanns-Seidel-Platz 4 81737 München, Germany info.silicones@wacker.com

www.wacker.com

Technical data sheet for ELASTOSIL® RT 774 / Version: 1.7 / Date of last alteration: 26.01.2016

WACKER

WACKER® CATALYST T 77

Product description

Catalyst paste for crosslinking condensation-curing two-part silicone rubber grades (RTV 2).

Special features

- thixotropic paste
- fast curing at room temperature
- cured rubbers show good self-adhesion to various substrates, such as metals, glass, ceramics, wood and plastics
- vulcanization times can be tailored by changing the mixing ratio

Application

WACKER® CATALYST T 77 is used and processed in combination with condensation-curing two-part silicone rubber grades (RTV-2). The vulcanization time can be adjusted to requirements by varying the ratios of components A and B.

The pot lives listed below indicate the time within which the material still spreads at 23 °C and 50 % r.h.

Varying the mixing ratio of components A and B within the range indicated above generally has little effect on the mechanical properties of the cured rubber. However, if the ratios are changed substantially, preliminary tests should be carried out to determine the material properties.

The cured rubber obtained with WACKER® CATALYST T 77 and the above-mentioned A component adheres well to a broad range of materials. For many substrates, the adhesive strength is generally independent of the type of A component used. The processor must carry out preliminary tests to determine the optimum conditions for a particular application. Detailed instructions for preparation and use are given in the product data sheet "WACKER RTV-2 Silicone Rubber – Processing."

Substrate	Adhesive strength
Glass, aluminum, stainless steel	Very good
Softwood	Usually very good
Polyamide 6	Good to very good
Others, such as polyamide 66 or PBT	Various

Storage

The 'Best use before end' date of each batch is shown on the product label.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety notes

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site http://www.wacker.com.





Product data

Typical general characteristics	Inspection Method	Value
Product data (uncured)		
Color		black
Viscosity, dynamic at 23 °C	DIN EN ISO 3219	approx, 150000 mPa.s
Density at 23 °C, at 1013 hPa	EN/ISO 1183	1,0 g/cm ³
Pot lives/curing rates		
Mixing ratio, A : B		
Curing characteristics Fast ¹	8:1	15 - 30 min
Curing characteristics Fast ¹	12 : 1	35 - 60 min
Curing characteristics Medium ²	8 : 1	45 - 60 min
Curing characteristics Medium ²	12 : 1	100 - 120 min
Curing characteristics Slow ³	8 : 1	75 - 90 min
Curing characteristics Slow ³	12 : 1	> 120 min
Curing rates (tack-free)		
Mixing ratio, A : B		
Curing characteristics Fast ¹	8 : 1	0,75 - 1 h
Curing characteristics Fast ¹	12 : 1	1 - 2 h
Curing characteristics Medium ²	8 : 1	1,5 - 2 h
Curing characteristics Medium ²	12 : 1	5 - 6 h
Curing characteristics Slow ³	8 : 1	> 2,5 h
Curing characteristics Slow ³	12 : 1	> 6 h

¹e.g. in combination with A component ELASTOSIL[®] RT 426 or ELASTOSIL[®] RT 428 ²e.g. in combination with A component ELASTOSIL[®] RT K or ELASTOSIL[®] RT 563 ³e.g. in combination with A component ELASTOSIL[®] M 4503 or ELASTOSIL[®] M 4511

These figures are intended as a guide and should not be used in preparing specifications.

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.

The management system has been certified according to DIN EN ISO 9001 and DIN EN ISO 14001

WACKER® is a trademark of

Wacker Chemie AG. ELASTOSIL® is a trademark of Wacker Chemie AG. For technical, quality, or product safety questions, please contact:

Wacker Chemie AG Hanns-Seidel-Platz 4 81737 München, Germany info.silicones@wacker.com

www.wacker.com