

PROTECTIVE FILM DATA SHEET **3-340-C**

Type: 3-340-C

Thickness:	3 mil, nominal
Backing:	Low Density Polyethylene, Clear
Adhesive:	Water-Based Acrylic with tack of 5 to 9 oz./in.
Tensile Strength:	MD=3800 TD=3000
Elongation:	MD=470 TD=650

Technical Description

A medium tack protective masking for use in surface protection. This product consists of a low-density polyethylene backing, coated with a custom formulated water-based acrylic adhesive with a soft release.

Applications

- Anodized matte/satin aluminum
- Ceramic & vinyl flooring
- Fiberglass, glossy
- Fiberglass, matte
- Textured uncoated glass
- Granite
- Hardwood flooring
- High gloss painted metal
- Marble & solid surface
- Matte painted metal
- Matte polycarbonate

Test Methods:

ASTM D 882 Standard Test Method for Tensile and Elongation of Thin Plastic Sheeting.

PSTC – 1 Standard Test Method for Peel Adhesion of Pressure-Sensitive Tape -- 180 ° peel adhesion to Stainless Steel Panels, 20 minute dwell time.

Disclaimer: The physical properties listed above are typical values and are not to be considered as specifications. Our suggestions for use are based on tests we believe to be reliable. However, the purchaser must determine the suitability of the product for their intended use. Surface Armor LLC assumes no liability for claims beyond those outlined within our Limited Warranty, which includes replacement value of proven defective products.

© 2012-2015 Surface Armor LLC. All rights reserved. Surface Armor LLC is the owner of the Surface Armor® family of trademarks and logos included herein.

Surface Armor LLC
2007A Industrial Blvd
Rockwall, Texas 75087
Tel: 972-722-7351
Fax: 972-722-7321
www.SurfaceArmor.com