

# LOCTITE NS 5540 KNOWN AS X350729

JANUARY 2018

## PRODUCT DESCRIPTION

LOCTITE® NS 5540 provides the following product characteristics:

<b>Technology</b>	Sealant
Chemical Type	Thermally Reactive
Appearance	Brown Liquid
<b>Cure</b>	Heat Cure
<b>Application</b>	Sealant for Threads and Flanges
Application Temperature	15 to 30 °C (59 to 86 °F)
Service Temperature	38 to 700 °C (100 to 1,300 °F)
Strength	High
Specific Benefits	<ul style="list-style-type: none"> <li>• One component</li> <li>• Low Viscosity</li> <li>• Chemical Resistant</li> </ul>

LOCTITE® NS 5540 is a thermal reactive liquid sealing compound that is used in high temperature and high pressure applications. In the presence of heat, LOCTITE® NS 5540 will form a "mechanical type" seal. LOCTITE® NS 5540 will not cement the flanges together, thus, it will not interfere with future repairs of metal-to-metal joints. LOCTITE® NS 5540 is unaffected by thermal cycling. This product has been successfully used to seal flanges carrying up to 2900 psi steam.

## TYPICAL PROPERTIES OF UNCURED MATERIAL

Density @ 25 °C	Lb/gal	8.08
Viscosity Brookfield- DV-E	mPa·s (cP)	48,450
K-Factor at 55 Ksi		0.14
Flash Point		See SDS

## TYPICAL CURING PROFILE

@ 200 °F (93 °C)	hours	36
@ 300 °F (149 °C)	hours	12
@ 400 °F (204 °C)	hours	8
@ 500 °F (260 °C)	hours	3
@ 600 °F (316 °C)	hours	2
@ 700 °F (370 °C)	hours	1

## TYPICAL PERFORMANCE OF CURED MATERIAL

Breakloose Torque, ISO 10964 1.25 inch dia, 7 pitch, B-7 Bolt w/ 2H Nut Ambient (215 make-up torque)	Ft*Lb	160
Breakloose Torque, ISO 10964 1.25 inch dia, 7 pitch, B-7 Bolt w/ 2H Nut 1,300 °F (215 make-up torque)	Ft*Lb	100
Threaded Connector Test, seal confirmation 1300°F/100 psi / 1 hour		Pass

## TYPICAL ENVIRONMENTAL RESISTANCE

Tables below show chemical resistance:

### Alkalis

		Temperature	24 hrs
Sodium Hydroxide	10 %	80 °C	Suitable

### Solvents

		Temperature	24 hrs
Water/Steam	100%	107 °C	Suitable
Isopropanol	100%	80 °C	Suitable

### Hydrocarbons

		Temperature	24 hrs
ISOPAR M	100%	80 °C	Suitable
Transmission Fluid	100%	107 °C	Suitable

## GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials. For safe handling information on this product, consult the Safety Data Sheet (SDS).

## DIRECTIONS FOR USE

### Surface Preparation

Remove dirt, oil, grease etc. with a suitable cleaner, e.g. Loctite® SF 7840™ (Loctite® Natural Blue® cleaner/degreaser).

### Application

1. Surface should be clean and dry (free from oil or foreign material to ensure proper sealing/adhesion)
2. Apply a thin coat to sealing surface with brush (if sealing threads, apply only to the male threads)
3. Close and tighten joint (torqued to the equipment manufacturer's specifications if sealing a bolted flange)
4. Product will cure in service with heat (See Note)

Note: In high pressure applications or when pressure testing at ambient, it is recommended to pre-cure with a heat gun, oven, or to dry fire / blow down at atmospheric (running heat without pressure). Unlike silicone or epoxy products, our thermosetting sealants require heat to cure.

### Clean-up

Immediately after use, clean tools with suitable cleaner, e.g. Loctite® SF 7070™ or a solvent such as acetone or Isopropyl alcohol. Once cured, the material can only be removed mechanically.

### Storage

The product is classified as flammable and must be stored in an appropriate manner in compliance with relevant regulations. Do not store near oxidizing agents or combustible materials. Store product in the unopened container in a dry location. Storage information may also be indicated on the product container labelling.

**LOCTITE NS 5540  
KNOWN AS X350729**

JANUARY 2018

**Optimal Storage: 8 to 21 °C (50 to 70 °F) . Storage below 8°C or greater than 28°C can adversely affect product properties.**

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

**Shelf Life of Unopened Container:**

24 months

**Conversions** $(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$  $\text{kV/mm} \times 25.4 = \text{V/mil}$  $\text{mm} / 25.4 = \text{inches}$  $\mu\text{m} / 25.4 = \text{mil}$  $\text{N} \times 0.225 = \text{lb}$  $\text{N/mm} \times 5.71 = \text{lb/in}$  $\text{N/mm}^2 \times 145 = \text{psi}$  $\text{MPa} \times 145 = \text{psi}$  $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$  $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$  $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$  $\text{mPa}\cdot\text{s} = \text{cP}$ **Note**

The information provided in this Laboratory Data Sheet (LDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this LDS. As this is an experimental product, the data is **for reference only** and should not be taken as specifications.

The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada, Inc. the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage**

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office."

Reference **N/A**