

# Glyptal Inc.

305 Eastern Avenue  
Chelsea, Massachusetts 02150

Telephone (617) 884-6918  
Fax (617) 884-8376

## PRODUCT DATA SHEET CE237

### DESCRIPTION

GLYPTAL CE-237 GLOSS BLACK is an air-drying or baking enamel. This material has very good oil, chemical, and corrosion resistance. It offers a tough durable film along with excellent arc resistance.

### SUGGESTED USES

GLYPTAL CE-237 is designed for the finishing of motor end windings. This material is an offset to 7815 and has improved arc resistance.

### PRODUCT DETAILS

Color	Black
Solids by Weight Avg.	50.0%
Air Dry- Tack Free	3 hours
Hard	Overnight
Bake Time: @ 125 °C	10-20 min
@ 95 °C	20-30 min
@ 65 °C	45-60 min
Gloss	High
Flash Point	< 80 °F
Coverage (approximate)	675 ft. <sup>2</sup> /gal (1 mil dried film)

### APPLICATION

GLYPTAL CE-237 may be applied by spray or dip methods. This material must be kept well agitated during use. Surfaces to be painted should be clean and dry.

*Reduction: Spray:* Thin to 25-30 seconds (#2 Zahn Cup) with 1500 Thinner.

*Dip:* Thin to 23-28 seconds (#2 Zahn Cup) with Solvesso 100.

### SURFACE PREPARATION

Surfaces to be painted should be dry and free from dirt, wax, grease, rust, and oil. Remove grease and oil by washing surface with mineral spirits.

### HAZARDS

Keep away from heat, sparks, and open flame. Avoid prolonged contact with skin and breathing of vapor or spray mist. Close container after each use. Use with adequate ventilation.

**KEEP OUT OF THE REACH OF CHILDREN.**

The recommendations, test results and suggestions are offered as a guide and are not a guarantee of the performance inasmuch as the company has no control over the use to which others may put the product. The above properties are typical values and not intended for specification use.