



# TYPICAL PROPERTIES & SPECIFICATIONS SHEET

conductive containers, inc.

**DESCRIPTION:** Inherently Dissipative TPU  
Permanent

**APPLICATION:** Thermoforming  
Long Term Use

**CCI PART NUMBER: KleanStat Flex TPU**

PROPERTY	VALUE (U.S.)	TEST METHOD
Volume Resistivity	10 <sup>8</sup> -10 <sup>10</sup> Ohms/cm	ESD S11.12
Surface Resistance	10 <sup>8</sup> -10 <sup>10</sup> Ohms/sq	ESD S11.11(12% RH)
Static Decay Rate (+5000V-50V)	0.01 Sec	FTMS 101-C (12% RH)
Static Decay Rate (-5000V-50V)	0.01 Sec	FTMS 101-C (12% RH)
Static Decay Rate (+1000V-100V)	0.1 Sec	FTMS 101-C (12% RH)
Host Polymer	TPU	-----
Filler	IDP	-----
Color	Transparent	Visual
Specific Gravity	1.16 g/cc	ASTM D-792
Tensile Modulus (@ 100%)	1,200 psi	ASTM D-412
Tensile Modulus (@ 300%)	2,200 psi	ASTM D-412
Tensile Strength (Break)	3,800 psi	ASTM D-412
Tensile Elongation (Break)	450%	ASTM D-412
Shore Hardness	90 A/47 D Shore	ASTM D-2240

### CHARACTERISTICS:

- Inherently Static Dissipative
- Melting Temperature: 355 °F
- Ultra-clean: low off-gassing and low ionic contamination
- Rated for 75 °C repeated use
- Available Gauges: .125-.150

### APPLICATIONS:

- Medical device packaging
- Electronic component handling
- Hard disk drive component packaging
- Superior cushioning

All values are for pre-formed materials. Electrical values will vary with each individual design.

All information, recommendations and suggestions appearing in this bulletin concerning the use of our products are based upon tests and data believed to be reliable; however, it is the user's responsibility to determine the suitability for their own use of the products described herein. Since the actual use by others is beyond our control, no guarantee, expressed or implied, is made by Conductive Containers, Inc. as to the effects of such use or the results to be obtained, nor does Conductive Containers, Inc. assume any liability arising out of use, by others, of the products referred to herein. Nor is the information herein to be construed as absolutely complete since additional information may be necessary or desirable, when particular or exceptional conditions or circumstances exist or because of applicable laws or government regulations. Nothing herein contained is to be construed as permission or as a recommendation to infringe any patent.