

LOCTITE® EA 3501HT

September 2020

PRODUCT DESCRIPTION

LOCTITE® EA 3501HT provides the following product characteristics:

Technology	Ероху
Chemical Type	Epoxy
Appearance	Grey paste
Components	One component - requires no mixing
Viscosity	High
Cure	Heat cure
Application	Seam sealing

LOCTITE® EA 3501HT is a one component, heat curing epoxy seam sealant designed for use on primed or bare, oily metal in preparation for high temperature paint bake processing which includes metal pre-treatment, e-coat/primer paint and powder/top-coat stages. This material is compatible with most metal pre-treatment processes and is formulated to maintain its physical properties and performance even after paint bake processes reaching 225°C.

LOCTITE® EA 3501HT is flexible and suitable for use on wide a range of substrate gauges ranging from thin sheet metals to rigid castings and extrusions.

Typical applications include sealing of metal seams between welded/bonded joints, overlap joints, butt joints, and any other visible seam which requires sealing.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Specific Gravity @ 23°C, ASTM D927	1.35
Viscosity @ 25 °C, mPa·s (cP):	
CP25-2, oscillation	480,000
Solids Content, ASTM D2834, %	100
Sag Resistance, SAE J243, mm:	
Vertical Sag Method B	0
Horizontal Sag Method B	0

TYPICAL CURING PERFORMANCE Cure Cycle

Typical Cure @ 175°C, minutes	30
Max Cure @ 225°C, minutes	30
Min Cure @ 160°C, minutes	30

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties

Shore Hardness, Durometer A 75
Low Temp Mandrel Bend @ -40°C, No cracking (SAE J1243 Method B (50mm diameter)) or adhesion loss

Adhesive Properties

Substrate Adhesion, Bead-knife, %:
Oily bare steel 10W-30, Epoxy primer paint >95

Epoxy Primer Valspar, EEY0148/CEC0120, %: Initial >95

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

Directions for use

- 1. This product is not frost sensitive.
- 2. Remove product from refrigeration and allow to reach ambient temperature before use.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 2 to 25°C . Storage below 2°C or above 25°C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel Representative.

Product Specification

The technical data contained herein are intended as reference only and are not considered specifications for the product. Product specifications are located on the Certificate of Analysis or please contact Henkel representative.



Approval and Certificate

Please contact Henkel representative for related approval or certificate of this product.

Data Ranges

The data contained herein may be reported as a typical value. Values are based on actual test data and are verified on a periodic basis.

Temperature/Humidity Ranges: 23° C / 50° RH = $23\pm2^{\circ}$ C / $50\pm5^{\circ}$ RH

Conversions

(°C x 1.8) + 32 = °F kV/mm x 25.4 = V/mil mm / 25.4 = inches N x 0.225 = lb/F N/mm x 5.71 = lb/in psi x 145 = N/mm² MPa = N/mm² N·m x 8.851 = lb·in N·m x 0.738 = lb·ft N·mm x 0.142 = oz·in mPa·s = cP

Disclaimer

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits. The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1

