

## PRODUCT DESCRIPTION

LOCTITE® EA E-60NC is a flowable, industrial grade epoxy potting compound with extended work life. Once mixed, the two-part epoxy cures at room temperature to form a rigid, black encapsulant that is non-corrosive to metallic components on PC Boards and electronic assemblies. The fully cured epoxy provides excellent environmental and chemical resistance, and acts as an electrical insulator.

## TYPICAL APPLICATIONS

Designed for bonding, potting and encapsulating electrical components which are sensitive to corrosion. Used in electronic applications, for component attachment to boards, housing assembly and potting.

## PROPERTIES OF UNCURED MATERIAL

Resin	Typical	
	Value	Range
Chemical Type	Epoxy	
Appearance	Black liquid	
Specific Gravity @ 25°C	1.10	1.0 to 1.2
Viscosity @ 25°C, mPa.s (cP)	6,200	5,200 to 7,200
Flash Point (TCC), °C (°F)	>93 (>200)	


Hardener	Typical	
	Value	Range
Chemical Type	Amine	
Appearance	Pale yellow liquid	
Specific Gravity @ 25°C	1.00	0.9 to 1.1
Viscosity @ 25°C, mPa.s (cP)	13,000	12,000 to 14,000
Flash Point (TCC), °C (°F)	>93 (>200)	

Mixture	Typical Value
Appearance	Black Opaque
Specific Gravity @ 25°C	1.05
Mix Ratio (R:H) by Weight	100 to 91
by Volume	1 to 1

## TYPICAL CURING PERFORMANCE

### Cure speed

The graph below shows the shear strength developed over time on abraded, acid etched aluminum lap shears with an average bondline gap of 3 to 9 mils and tested according to ASTM D-1002.



## Curing Properties

(@ 25°C unless noted)	Typical Value
Working Life, minutes	60
Tack Free time, minutes	180

## TYPICAL PROPERTIES OF CURED MATERIAL

(@ 25°C unless noted)	Typical Value
<b>Physical Properties</b>	
Dielectric Strength, Volts/Mil	550
Tensile Strength ASTM D638, psi	6,800
Tensile Elongation ASTM D-638, %	8
Hardness ASTM D-1706, Shore D	85
Glass Transition Temperature, Tg, °C	55

## PERFORMANCE OF CURED MATERIAL

### Shear Strength vs Substrate

(Substrates cured for 5 days @ 22°C)

Substrate	Typical Value	
Lapshear	N/mm <sup>2</sup>	(psi)
Grit-Blasted Steel	18.1	2630
Aluminum (Abraded/Acid Etched, 3 to 9 mil gap)	21.4	3110
Aluminum (Anodized)	7.9	1150
Stainless Steel	7.8	1130
Polycarbonate	5.9	850
Nylon	1.3	190
Wood (Fir)	11.1	1610

### Block Shear


	N/mm <sup>2</sup>	(psi)
PVC	4.6	670
ABS	6.5	940
Epoxy	14.8	2140
Acrylic	1.2	180
Glass	13.9	2020

## TYPICAL ENVIRONMENTAL RESISTANCE

### Hot Strength


Test procedure : ASTM D-1002  
 Substrate: Abraded, acid etched aluminum  
 Bondline gap, mils: 3 to 9  
 Cure procedure: 12 hours at 65°C & 4 hours at 22°C

Tested at temperature.



### Heat Aging

Cured for 5 days at 22°C on steel with no induced gap, aged at temperature indicated and tested at 22°C.



### Chemical / Solvent Resistance

Cured for 5 days at 22°C on steel with no induced gap, aged under conditions indicated and tested at 22°C.

Solvent	Temp.	% Initial Strength retained at	
		500 hr	1000 hr
Air	87°C	108	110
Motor Oil (10W-30)	87°C	104	82
Unleaded Gasoline	87°C	96	101
Water/Glycol (50%/50%)	87°C	95	101
Salt/Fog ASTM B-117	22°C	59	85
95% Relative Humidity	38°C	102	100
Condensing Humidity	49°C	78	81
Water	22°C	89	94
Acetone	22°C	78	64
Isopropyl Alcohol	22°C	98	90

### GENERAL INFORMATION

**This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.**

**For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).**

### Directions for use

- For high strength structural bonds, removal of surface contaminants such as paint, oxide films, oils, dust, mold release agents and all other surface contaminants.
- Use gloves to minimize skin contact. DO NOT use solvents for cleaning hands.
- Dual Cartridges:** To use simply insert the cartridge into the application gun and start the plunger into the cylinders using light pressure on the trigger. Next, remove the cartridge cap and expel a small amount of adhesive to be sure both sides are flowing evenly and freely. If automatic mixing of resin and hardener is desired, attach the mixing nozzle to the end

of the cartridge and begin dispensing the adhesive. For hand mixing, expel the desired amount of the adhesive and mix thoroughly. Mix approximately 15 seconds after uniform color is obtained. **Bulk Containers:** Mix thoroughly by weight or volume in the proportions specified in Properties of Uncured Material section. Mix vigorously approximately 15 seconds after uniform color is obtained.

- For maximum bond strength apply adhesive evenly to both surfaces to be joined.
- Application to the substrates should be made within 60 minutes. Larger quantities and/or higher temperatures will reduce this working time.
- Join the adhesive coated surfaces and allow to cure at 25°C (77°F) for 24 hours for high strength. Heat up to 93°C (200°F), will speed curing.
- Keep parts from moving during cure. Contact pressure is necessary. Maximum shear strength is obtained with a 3-9 mil bond line.
- Excess uncured adhesive can be cleaned up with ketone type solvents.

### Storage

Product shall be ideally stored in a cool, dry location in unopened containers at a temperature between 8°C to 28°C (46°F to 82°F) unless otherwise labeled. Optimal storage is at the lower half of this temperature range. To prevent contamination of unused product, do not return any material to its original container. For further specific shelf life information, contact your local Technical Service Center.

### Data Ranges

The data contained herein may be reported as a typical value and/or range. Values are based on actual test data and are verified on a periodic basis.

### Note

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada, Inc. the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

#### **Trademark usage**

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.