

#### **CORROSION INHIBITING COMPOUNDS**

# COR-BAN<sup>®</sup> 23 ENHANCED DYE

# Product description: CORROSION INHIBITING COMPOUND

#### FEATURES:

- A long lasting, high penetration, and water displacing corrosion inhibiting compound
- Has a stronger dye than regular Cor-Ban<sup>®</sup> 23
- May be used in the place of Airbus CML 15-006

#### **KEY BENEFITS:**

- Free of chromates
- Free from heavy metals
- Low toxicity
- Offers inhibition and a thin film
- Water displacing
- Very low dry film weight <0.3 mil (8 microns) required to surpass specification</p>
- Non-cracking and non-flaking to -65°F (-54°C)
- Non-sagging, fast drying, non-tacky, and detectable film

Rev: 29124E 03-16-2022



For more information contact us : zipchem@addevmaterials.com

#### CORROSION INHIBITING COMPOUNDS

# COR-BAN<sup>®</sup> 23 **ENHANCED DYE**

### Product description: **CORROSION INHIBITING** COMPOUND

#### **KEY BENEFITS:**

- Solvent removable
- Strong dye allows for easy visual detection
- > 3000 Hours Salt Spray

#### SPECS:

- AIMS 09-08-001 Type I Grade 3
- BAMS 565-006 Type V
- BMS 3-23J Type II Class 2 Grade A & B (QPL)

#### **APPLICATIONS:**

- Apply by conventional airless, air-operated spray equipment, or by aerosol
- ✓ Use on high profile aircraft substrates, upper edge floor beams, wheel wells, pressure deck, and center wing sections
- ✓ The Cor-Ban<sup>®</sup> 23 Enhanced Dye aerosol can be used in conjunction with the Formit<sup>®</sup> extensions to provide targeted spray to areas that may be difficult to reach but need to be coated. Please refer to the Formit<sup>®</sup> technical data sheet for more information.
- ✓ All properties represented were achieved with a dry film thickness of range 0.3 0.5 mils (7-12 microns)
- ✓ The wet film will self level to achieve the desired dry film thickness when applied to an inclined surface
- ✓ One aerosol can covers approximately 160 ft<sup>2</sup> (14.9 m<sup>2</sup>) and one gallon (3.8L) of bulk material covers approximately 2290 ft<sup>2</sup> (56.2 m<sup>2</sup>/liter).



For more information contact us : zipchem@addevmaterials.com



- Fed-Ex E.O. 9-5100-7-5001
- BMS 3-35

# **Cor-Ban**®

#### **CORROSION INHIBITING COMPOUNDS**

# COR-BAN<sup>®</sup> 23 ENHANCED DYE



Product description: CORROSION INHIBITING COMPOUND

#### **PHYSICAL PROPERTIES:**

- **Color:** Transparent Reddish-Pink
- Drying Time: <1 hour</p>
- Exfoliation: Pass at -65°F (-54°C)
- **Flash Point:** 114°F (45°C)
- Low Temp Flaking: Pass
- Non-Volatiles: 42%
- Operating Temperature: -65°F (-54°C) to 350°F (177°C)
- Penetration: >4 inches per hours per BMS 3-35
- Salt Spray Protection: >3000 hours on aluminum
- Specific Gravity: 0.88
- Viscosity: 35-40 cps.
- Water Displacement: 0% Rust

#### AVAILABLE PACK SIZES:

- Case of 12 of 16 fl oz (473 ml) Aerosols-011321
- 5 Gallon (18.9L) Pail-011209
- Special Packaging Upon Request

For more information contact us : **zipchem@addevmaterials.com** 

