



# LOCTITE® EA 9807 AERO

January 2023

## PRODUCT DESCRIPTION

LOCTITE® EA 9807 AERO provides the following product characteristics:

<b>Technology</b>	Epoxy
Chemical Type	Epoxy
Appearance (Resin)	Purple
Appearance (Hardener)	Amber
Appearance (Mixed)	Purple
Components	Two components - requires mixing
Mix Ratio, by weight - Resin : Hardener	100 : 30
<b>Cure</b>	5 to 7 days @ 25°C (77°F)
Secondary Cure	Allow the material to Gel at ambient for a minimum of 60 minutes prior to the heat cure <ul style="list-style-type: none"> <li>• 90 minutes at 127°C (260°F)</li> <li>• 60 minutes at 177°C (350°F)</li> </ul>
<b>Application</b>	Potting or Edge Fill
Service Temperature	121°C (250°F)
Specific Benefits	<ul style="list-style-type: none"> <li>• Good for potting, edge filling</li> <li>• Pourable consistency</li> <li>• Flame retardant</li> <li>• Low exotherm temperature</li> <li>• Short gel time</li> <li>• Good high temp. properties</li> </ul>

LOCTITE® EA 9807 AERO is a two-part room temperature curing intermediate density structural epoxy syntactic flame-retardant potting compound for use on honeycomb assembly parts and repair applications.

## TYPICAL PROPERTIES OF UNCURED MATERIAL

### Part A Properties

Density, g/cm<sup>3</sup> 0.82

### Part B Properties

Density, g/cm<sup>3</sup> 0.96

### Mixed Properties

Density, g/ml 0.85

Viscosity, Brookfield- RVT @ 25°C, mPa·s (cP):

Spindle 6, speed 20 rpm 14,194

Pot life 100 gram mass, @ 25°C (77°F), in water 90 bath, ASTM D2471, minutes

Remark: Amine carbonate formation (surface tackiness) is normal after a room temperature cure when the uncovered cured epoxy is exposed to the environment. The surface is sandable with the surface tackiness after 8 hours at 25°C (77°F). To avoid surface tackiness, cover the epoxy with Teflon when curing at room temperature or heat cure the epoxy per manufacturing recommendation.

## TYPICAL CURING PERFORMANCE

### Recommended Curing Conditions

- 5 days @ 25°C (77°F)
- 90 minutes @ 127°C (180°F) after 60 min. at 25°C (77°F)
- 60 minutes @ 177°C (350°F) after 60 min. at 25°C (77°F)

Remark: For applications that require an elevated heat cure, allow the material to gel at ambient prior to exposing the material to elevated cure temperatures to prevent excessive cure temperatures.

This adhesive should be cured to the above minimum recommended cure condition to achieve normal performance.

The above cure profile(s) are guideline recommendation(s). These conditions (time and temperature) may vary based on customers' experience and specific application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

## TYPICAL PROPERTIES OF CURED MATERIAL

### Physical Properties

Shore Hardness Durometer D:

Cured 5 days @ 25°C (77°F) 70

Approx. 6.35 mm / 0.25 inch thick

Glass Transition Temperature <sup>(1)</sup>, °C:

Tg Dry (E'):

Cured 7 days @ 25°C (77°F)	67°C / 153 °F
Cured 90 minutes @ 127°C (260°F)	112°C / 233 °F
Cured 60 minutes @ 177°C (350°F)	107°C / 225 °F
Cured 14 days @ 177°C (350°F)	116°C / 241 °F

Coefficient of Thermal Expansion, ASTM E831-05

cure 7 days @ 25°C / 77 °F:

CTE 1 (before Tg), µm/m-°C	52.9
CTE 2 (after Tg), µm/m-°C	101.7

Flammability(15 second horizontal direction)

Sample dimension: 0.5 in<sup>3</sup> (12.7 mm<sup>3</sup>)

Cure Temp.	25°C (77°F)	127°C (260°F)	177°C (350°F)
Cure Time	7 days	90 minutes	60 minutes
Burn Rate, in/min. (cm/min.)	0.18 (0.46)	0.13 (0.33)	0.09 (0.23)
Burn Length, inch (cm)	1.5 (3.8)	1.4 (3.6)	1.3 (3.3)

Immersion(Percent absorption)

Sample dimension: 0.5 in<sup>3</sup> (12.7 mm<sup>3</sup>)

Fluid soak time: 24 hours at 25°C (77°F)

Cure temp.	25°C (77°F)	127°C (260°F)	177°C (350°F)
Cure time	7 days	90 minutes	60 minutes
TT-S-735 Type III	0.05	0.02	0.03
MIL-PRF-5606 Hydraulic	0.19	0.23	0.21
Skydrol LD4	0.22	0.26	0.19
Distilled Water	0.21	0.13	0.15

**Mechanical Properties**

Tensile Lap Shear Strength

- Test method per ASTM D1002
- Metal: 2024T-3 Clad, 0.063" (1.6mm) thick
- Phosphoric Acid Anodized per ASTM D3933
- Cured bondline thickness: 10 mils

Cured 7 days @ 25°C (77°F)	N/mm <sup>2</sup>	28.8
	(psi)	(4,175)
Cured 60 minutes @ 177°C (350°F)	N/mm <sup>2</sup>	27.8
	(psi)	(4,025)
Cured 14 days @ 177°C (350°F)	N/mm <sup>2</sup>	27.5
	(psi)	(3,990)

Bond Strength Performance

Compression Performance:

Test method per ASTM D695 (ISO 604)

Sample dimension: 0.5" x 0.5" x 1.0" (12.7mm x 12.7mm x 2.54mm)

Sample soak time at elevated test temperature was 10 min. at test temperature prior to testing

Cure temp.	25°C (77°F)	177°C (350°F)	177°C (350°F)	177°C (350°F)	177°C (350°F)
Cure time	7 days	60 minutes	14 days	60 minutes	14 days
Ultimate strength, ksi (MPa)	(10.7) 73.5	(12.5) 86.2	(14.3) 98.9	(1.6) 10.9	(1.3) 9.0
Modulus, ksi (MPa)	(396) 2733	(360) 2480	(428) 2954	(22) 152	(14) 98

<sup>1</sup> Rheometric Scientific DMTA IV, heat-up rate: 5°C/min., frequency: 1 Hz, strain: 0.1%, sample dimension: 25.4 mm / 1 inch x 12.4 mm / 0.49 inch x 1.6 mm / 0.063 inch.

**GENERAL INFORMATION**

**This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.**

**For safe handling information on this product, consult the Safety Data Sheet (SDS).**

**PRECAUTIONARY INFORMATION**

As with most epoxy based systems, use this product with adequate ventilation. Do not get in eyes or on skin. Avoid breathing the vapors. Wash thoroughly with soap and water after handling. Empty containers retain product residue and vapors so obey all precautions when handling empty containers.

**CAUTION!** This material may cause eye and skin irritation or allergic dermatitis. It contains epoxy resins.

**WARNING!** This material causes eye and skin irritation or allergic dermatitis. It contains amines.

Before using this product refer to container label and HENKEL TECHNOLOGIES MATERIAL SAFETY DATA SHEET for additional precautionary, handling and first aid information.

**DIRECTION FOR USE:****Mixing:**

1. Mixing the individual adhesive component just prior to use is recommended. The temperature of the separate components prior to mixing is not critical, but should be close to room temperature: 25°C (77°F).
2. Combine 100 parts resin to 31 parts hardener by weight and mix thoroughly.
3. Do not mix quantities greater than 450 grams as dangerous heat buildup can occur causing uncontrolled

decomposition of the mixed adhesive. Toxic fumes can occur, resulting in personal injury.

- Mixing smaller quantities will minimize the heat buildup.

#### Mixing Procedure:

Mix Type	Mass	Mix Time	Mix Speed
by centrifuge	≤200 grams	30 seconds	1000 rpm
	400 grams	30 seconds	1500 rpm
by hand	≤100 grams	2-3 minutes	Slow
	300 grams	5 minutes	Slow

Remark: Centrifuge mixing is the preferred method for mixing. If mixing by hand, slowly mix both components to reduce frothing.

#### Application:

- Bonding surfaces should be clean, dry and properly prepared.
- The bonded parts should be held in contact until the adhesive is set.
- Handling strength for this adhesive will occur in 24 hours at 25°C (77°F), after which the support tooling or pressure used during cure may be removed. Since full bond strength has not yet been attained, load application should be small at this time.

#### Clean-up:

- It is important to remove excess adhesive from the work area and application equipment before it hardens.
- Denatured alcohol and many common industrial solvents are suitable for removing uncured adhesive.
- Consult your solvent supplier's information pertaining to the safe and proper use of solvents.

#### Disposal:

- Dispose of spent remover and paint residue per local, state and regional regulations. Refer to HENKEL TECHNOLOGIES MATERIAL SAFETY DATA SHEET for additional disposal information.

#### Henkel QC Acceptance Testing

This data sheet provides users with typical properties obtained from this adhesive. These values are not meant to be used to develop aerospace QC acceptance testing. Users interested in establishing values and tests for routine QC acceptance should request our internal specifications (DAS), which provides detailed test methods and values used to certify this adhesive.

#### Service Temperature

Service temperature is defined as that temperature at which this adhesive still retains 1000 psi/6.9 MPa using test method ASTM D1002 and is 121°C/250°F.

#### STORAGE

Store product in the unopened container in a dry location. Storage information is indicated on the product container labeling.

**Optimal Storage: 8 to 28 °C. Storage greater than 28 °C can adversely affect product properties.**

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously recommended. If additional information is required, please contact your local Henkel Representative.

#### DATA RANGES

The data contained herein may be reported as a typical value. Values are based on actual test data and are verified on a periodic basis.

#### Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$   
 $\text{kV/mm} \times 25.4 = \text{V/mil}$   
 $\text{mm} / 25.4 = \text{inches}$   
 $\mu\text{m} / 25.4 = \text{mil}$   
 $\text{N} \times 0.225 = \text{lb}$   
 $\text{N/mm} \times 5.71 = \text{lb/in}$   
 $\text{N/mm}^2 \times 145 = \text{psi}$   
 $\text{MPa} \times 145 = \text{psi}$   
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$   
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$   
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$   
 $\text{mPa}\cdot\text{s} = \text{cP}$

## Disclaimer

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

### Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

### Reference 1.0