

(KNOWN AS TURCO MIL-ETCH)

Issued: 12/17/2018

### INTRODUCTION:

BONDERITE C-AK MIL-ETCH AERO (known as TURCO MIL-ETCH) is a granular alkaline product formulated to produce a fine satin or frosted etch on aluminum and its alloys. The working solution develops a low level foam blanket to prevent caustic mist from escaping into the workplace.

BONDERITE C-AK MIL-ETCH AERO (known as TURCO MIL-ETCH) provides outstanding sequestering action which prevents a build-up of scale and sludge on tank walls and heating coils. These benefits eliminate the need for expensive descaling of the tank and the heating coils and assures efficient heating of the etch bath.

### **OPERATING SUMMARY:**

Recommended operating conditions for BONDERITE C-AK MIL-ETCH AERO (known as TURCO MIL-ETCH) are:

Chemical:	Bath Preparation per 100 gallons		
BONDERITE C-AK MIL-ETCH AERO (known as TURCO MIL-ETCH)	25 - 50 lbs.		
General Operation and Control:			
Concentration:	4 - 8 oz/gal (30 - 60 g/L)		
Temperature:	100 - 160°F (37-72°C)		
Time:	5 - 10 minutes (Optimum)		
BAC 5786 Operation and Control:  **Approved for BAC 5786 use as an additive only			
Concentration:	3 - 5 oz/gal (22.5 - 37.5)		
Temperature:	90 - 110°F (32 - 43°C)		
Time:	5 - 10 minutes (Optimum)		

NOTE: See Chart for Aluminum and BONDERITE C-AK MIL-ETCH AERO (known as TURCO MIL-ETCH) guidelines.





(KNOWN AS TURCO MIL-ETCH)

### PROCESS:

- 1. Clean, using an appropriate Henkel cleaner
- 2. Water rinse
- 3. Etch in BONDERITE C-AK MIL-ETCH AERO (known as TURCO MIL-ETCH)
- Water rinse
- Desmut/Deox in BONDERITE C-IC 2310 AERO (known as Deoxalume 2310), etc.
- 6. Water rinse
- 7. Anodize, inspection, etc.

### **MATERIALS:**

- 1. BONDERITE C-AK MIL-ETCH AERO (known as TURCO MIL-ETCH)
- 2. Testing reagents and apparatus

#### **EQUIPMENT RECOMMENDATIONS:**

Mild steel or 300 Series stainless tanks and heating equipment are suitable for BONDERITE C-AK MIL-ETCH AERO (known as TURCO MIL-ETCH). Tank ventilation should be provided to control caustic fumes from hot solutions.

### SURFACE PREPARATIONS:

### Cleaning:

To ensure a uniform etch in the bath containing BONDERITE C-AK MIL-ETCH AERO (known as TURCO MIL-ETCH), aluminum work pieces must be thoroughly cleaned using a nonsilicated cleaner prior to being placed in the etch bath. A mild etching alkaline cleaner such as BONDERITE C-AK 298 AERO (known as Ridoline 298) is recommended.

## Water Rinsing:

After cleaning, the metal must be thoroughly rinsed with water, preferably warm. The rinse should be overflowed continuously at a rate which will keep it clean and free from scum and contamination.

### TREATING WITH THE BONDERITE C-AK MIL-ETCH AERO (known as TURCO MIL-ETCH) SOLUTION:

#### <u>Buildup</u>

25 to 50 pounds of BONDERITE C-AK MIL-ETCH AERO (known as TURCO MIL-ETCH) per 100 gallons of solution.

For BAC 5786 operation, add 19 to 31 pounds of BONDERITE C-AK MIL-ETCH AERO (known as TURCO MIL-ETCH) per 100 gallons.

Fill the tank about three-fourths full with water. Slowly add the proper amount of BONDERITE C-AK MIL-ETCH AERO (known as TURCO MIL-ETCH) and circulate. Add sufficient water to bring solution up to working level and heat to operating temperature.

### **Operation:**

Time: 5 to 10 minutes.

Temperature: 100° - 160° Fahrenheit.

90° - 110° Fahrenheit for BAC 5786

After the best conditions for concentration, time and temperature have been established they should be maintained closely. Temperature should be held within  $\pm$  5° Fahrenheit.





(KNOWN AS TURCO MIL-ETCH)

### **TESTING AND CONTROL:**

Free Caustic Soda:

### **Concentration Titration:**

- 1. Pipette a 10 mL sample of etch bath into a clean 250 mL Erlenmeyer flask.
- 2. Add 50 mL of water and 4 drops of Indicator 3 (Phenolphthalein). Solution should be pink to red.
- 3. Titrate with Titrating Solution 60 (1.0N hydrochloric acid) until the pink or red color disappears. Record the number of mL of Titrating Solution 60 required.
- 4. Concentration Calculation:

oz/gal of BONDERITE C-AK MIL-ETCH AERO (known as TURCO MIL-ETCH) =  $0.52 \times mL$  of T.S. 60 from step 3 g/L of BONDERITE C-AK MIL-ETCH AERO (known as TURCO MIL-ETCH) =  $3.93 \times mL$  of T.S. 60 from step 3

## **Aluminum Content Titration:**

- 1. Filter sample of etch bath (enough for step 2) through Whatman 54 filter paper.
- 2. Pipette a 10 mL sample of the clear, filtered solution into a clean 250 mL Erlenmeyer flask.
- 3. Add 50 mL of water.
- 4. Titrate with Titrating Solution 60 until the first permanent cloudiness or turbidity is detected.

#### Note:

A precipitate will form as the Titrating Solution #60 is added, but the precipitate will dissolve and leave the solution cloudy.

- 5. Record the number of mL of Titrating Solution 60 required to reach the turbid end point Do Not zero burette.
- 6. Add 4 drops of Indicator 3 (Phenolphthalein).
- 7. Continue titrating with Titrating Solution 60 (1.0N hydrochloric acid) until the pink color disappears. Record the number of mL of Titrating Solution 60 used to reach this endpoint.
- 8. For calculation below mL of T.S. 60 = mL from step 7 mL from step 5
- 9. Aluminum Calculation:

oz/gal of Aluminum = 0.36 x mL of Titrating Solution 60 g/L of Aluminum = 2.67 x mL of Titrating Solution 60

### Note:

It may be difficult to filter the etch bath after the aluminum content exceeds 100 g/L. In this case, take a 50 mL sample of the etch bath, dilute with 50 mL of D.I. water and proceed as noted above. Multiply the mL of T.S. #60 required to reach the turbid end point by 2 to get the correct results.

## STORAGE:

BONDERITE C-AK MIL-ETCH AERO (known as TURCO MIL-ETCH) should be stored in sealed containers located in a cool dry, ventilated area away from acidic materials. Keep containers tightly closed when not in use. If the drums are left open, the product will absorb moisture from the air and caking will result. Do not mix with flammable liquids, organic halogens or soft metals.





(KNOWN AS TURCO MIL-ETCH)

### **DISPOSAL INFORMATION:**

BONDERITE C-AK MIL-ETCH AERO (known as TURCO MIL-ETCH) will require neutralization to a specified pH range depending on Federal, State and local waste treatment regulations.

### PRECAUTIONARY INFORMATION:

BONDERITE C-AK MIL-ETCH AERO (known as TURCO MIL-ETCH) contains highly alkaline materials and is corrosive. Contact with skin or eyes may cause severe irritation or burns. The same safety precautions should be observed as when handling caustic type materials. Personnel should wear eye protection, NIOSH approved air mask, rubber gloves and apron or other protective clothing when working with BONDERITE C-AK MIL-ETCH AERO (known as TURCO MIL-ETCH). Tanks used for BONDERITE C-AK MIL-ETCH AERO (known as TURCO MIL-ETCH) should be provided with an adequate exhaust system to protect workers against irritating or corrosive airborne contaminants. Material Safety Data Sheets are available upon request from Henkel Surface Technologies.

BONDERITE C-AK MIL-ETCH AERO (oz/gal)	5.0	5.5	6.1	6.6	7.2	7.8	8.3	8.8	9.4	10.0	10.6
Dissolved Aluminum (g/L)	0	20	40	60	80	100	120	140	160	180	200



\*Note: This chart shows the amount of dissolved aluminum the bath can hold per concentration.





(KNOWN AS TURCO MIL-ETCH)

### **TESTING REAGENTS AND APPARATUS**

(Order only those items which are not already on hand.)

<u>Code</u>	Quantity	<u>Item</u>
592477	1	Buret assembly, 25 mL automatic
592488	2*	Flask, Erlenmeyer, 250 mL
592475	1	Indicator dropping bottle
592492	2*	Pipette, 10 mL volumetric
592494	1	Pipette filler
592398	1 qt	Indicator 3 (Phenolphthalein)
592440	1 gal	Titrating Solution 60 (1.0N HCI)

<sup>\*</sup>Includes one more than actually required, to allow for possible breakage.

Henkel Corporation | 32100 Stephenson Highway | Madison Heights, MI 48071 PHONE: (248) 583-9300 | FAX: (248) 583-2976 | www.henkelna.com/

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits. The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

