

Bluesil™ RTV 1597

October 2017

Addition Cure Silicone Elastomer

Description

Bluesil™ RTV 1597 is a two component, medium hardness, high strength, addition cure, room temperature or heating curing silicone elastomer. Designed specifically for moldmaking application, it offers low viscosity, high tear and cut resistance, and easy release for long lasting molds.

Bluesil™ RTV 1597 has high temperature and chemical resistance with excellent flexibility, low shrinkage, and well-defined detail reproduction, making it ideal for prototyping applications.

Applications

- Conventional production and prototype molds
- Finish rubber parts
- Stereolithography (SLA) molds
- Picture frames, mirrors, and furniture molding
- Giftware, furniture, and artistic molding
- Electronic encapsulation
- Epoxy laminate molding

Typical Properties

AS SUPPLIED		CATALYZED PROPERTIES	
<u>Part A - Base Component</u>		Mixed at 24°C (75°F) and 50% R.H.	
• Color	Translucent	• Mix Ratio, A:B (Parts by weight)	10:1
• Consistency	Pourable	• Viscosity, cP. (mPa.s)	15,000
• Viscosity, cP. (mPa.s) ⁽¹⁾	20,000	• Pot Life, hrs. ⁽²⁾	2
<u>Part B – Catalyst Component</u>		• Work Life, minutes ⁽³⁾	60
• Color	Blue or Translucent	• Demold Time, hrs. at R.T.	16-24
• Viscosity, cP. (mPa.s)	10,000		
CURED RUBBER , Cured 7 days at 24°C (75°F) and 50% RH			
PROPERTY	TEST METHOD	VALUE	
• Specific Gravity		1.1	
• Hardness, Shore A	ASTM D2240	38	
• Tensile Strength, psi (N/mm ²)	ASTM D412	950 (6.5)	
• Elongation, %	ASTM D412	550	
• Tear Strength, ppi (N/mm)	ASTM D624, Die B	110 (19)	
• Linear Shrinkage, % ⁽⁴⁾ , 24 Hours		<0.1	
7 Days		0.1	
• Temperature Range, °C (°F)		-55 to 249 (-65 to 400)	
• Coverage, cc. in/lb (cc/kg)		25.2 (909)	
• Thermal Conductivity, cal/cm ² ×sec×°C/cm		5.94 x 10 ⁻⁴	
Btu/ft ² ×hr×°F/in		1.7	
W/m ² K		0.25	
CURE SCHEDULE , Time required to develop cured properties;			
3 days at 24°C (75°F); 30 minutes at 100°C (212°F); 2 hours at 65°C (150°F); 15 minutes at 150°C (300°F).			
(1) May become slightly thixotropic: this is quickly corrected by agitation.			
(2) Time at which material gels.			
(3) Time required to double initial catalyzed viscosity			
(4) 8x8x0.25 in (20.3x20.3x0.64 cm) molded sheet, cured at room temperature			
TYPICAL ELECTRICAL PROPERTIES			
• Dielectric Strength, V/mil (kV/mm)	460(18.2)		
• Dielectric Constant, 1kHz	3.0		
• Dissipation Factor, 1kHz	0.004		
• Volume Resistivity, ohm×cm	7.1 x 10 ¹⁴		

Please note: The typical properties listed in this data sheet are not intended for use in preparing specifications for any particular application of BLUESIL™ silicone materials. Please contact our Technical Service Department for assistance in writing specification.

Bluesil™ RTV 1597

Storage and shelf life	When stored in its original packaging at a temperature of 24°C (75°F), Bluesil™ RTV 1597 may be stored for up to 18 months from its date of manufacture. Beyond this date, Bluestar Silicones no longer guarantees that the product meets the sales specifications.
Safety	Please consult the Safety Data Sheet of Bluesil™ RTV 1597 . The curing agent for this material can generate flammable gas upon contact with acidic, basic, or oxidizing materials. Precautions to avoid contact of this curing agent with these materials should be exercised.
Packaging	Bluesil™ RTV 1597 is available in 18kg and 180 kg containers.

Bluesil™ is a registered Trademark of **Elkem SILICONES**

 EUROPE	 NORTH AMERICA	 LATIN AMERICA	 ASIA PACIFIC
<i>Elkem Silicones France</i> 21 Avenue Georges Pompidou F69486 Lyon Cedex 03 FRANCE Tel. (33) 4 72 13 19 00 Fax (33) 4 72 13 19 88	<i>Elkem Silicones USA</i> Two Tower Center Boulevard Suite 1601 East Brunswick, NJ 08816-1100 United States Tel. (1) 732 227 2060 Fax (1) 732 249 7000	<i>Elkem Silicones Brazil Ltda.</i> Av. Maria Coelho Aguiar, 215 Bloco G - 1º Andar 05804-902 - São Paulo - SP - Brazil Tel. (55) 11 3747 7887 Fax (55) 11 3741 7718	<i>Elkem Silicones Hong Kong</i> Trading Co. Ltd. Unit C, 18/F Manulife Tower 169 Electric Road North Point-Hong Kong Tel. (852) 3106 8200 Fax (852) 2979 0241
<u>Warning to the users</u> The information contained in this document is given in good faith based on our current knowledge. It is only an indication and is in no way binding, particularly as regards infringement of or prejudice to third party rights through the use of our products. Elkem SILICONES guarantees that its products comply with its sales specifications. This information must on no account be used as a substitute for necessary prior tests which alone can ensure that a product is suitable for given use. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorizations. Users are requested to check that they are in possession of the latest version of this document and Elkem SILICONES is at their disposal to supply any additional information.			