

Technical Information

TI/N-CPN/IP Plastomoll® DOA
April 2021

Page 1 of 4

Supersedes edition dated June 2019

Petrochemicals Plasticizers



Plastomoll® DOA

Plasticizer for PVC, surface coatings and rubber. Especially suited for flexible PVC colorants and coatings requiring good low-temperature properties. Plastomoll® DOA meets the requirements for good packaging and can, therefore, be used for flexible PVC films for food contact (cling film).

Chemical Nature

Diethyl adipate

Product Number

50000025

BASF Registered Name

Plastomoll® DOA

CAS No.

103-23-1


Molecular Weight

371

Formula

C₂₂H₄₂O₄

Molecular Structure



where R = C₈H₁₇

Product Specifications

	Value	Test Method
Specific gravity @ 25°/25 °C	0.923 - 0.927	ASTM D-4052
Ester content, % by area (minimum)	99.6	ASTM D-3465
Acid Number, mg KOH/g (maximum)	0.1	ASTM D-1045
Water, % by weight (maximum)	0.1	ASTM E-203
Color, Pt-Co Units (APHA, maximum)	25	ASTM D-5386
Suspended Matter	COLSFFM*	visual

*Clear Oily Liquid Substantially Free of Foreign Material

Typical Physical Properties

The following data were measured in the BASF Corp. laboratory. They do not represent any legally-binding guarantee of properties for our sales product

		Value
Vapor Pressure @ 20 °C, mbar		< 0.01
Pour point, °C		-75
Solubility @ 25 °C in water, mg/L		< 0.01
Flash point (COC), °C		199
	Dynamic viscosity [cP]	Density [g/cm ³]
@ -40 °C	760	0.972
@ -30 °C	280	0.964
@ -20 °C	122	0.956
@ -10 °C	60.9	0.949
@ 0 °C	34.1	0.941
@ 10 °C	21.0	0.933
@ 20 °C	13.8	0.926
@ 40 °C	7.08	0.911
@ 60 °C	4.25	0.896
@ 80 °C	2.84	0.881
Odor	mild characteristic	
Surface Tension, mN/m,	30.3	
Solution Temperature, °C,	144	
Plastisol Gelation Temperature, °C	140	

Description

Plastomoll® DOA is a highly efficient plasticizer which imparts excellent low temperature flexibility and resistance to impact to the base resin. For these reasons it finds wide use in polymeric systems based on vinyl, nitrocellulose and rubber. It is extensively used in food contact applications.

In addition to its high efficiency and contribution to the low temperature properties of vinyl, Plastomoll® DOA is chemically stable and resistant to discoloration on extended exposure to heat and ultraviolet light.

The combination of low viscosity and efficiency provide excellent dry blending and processing characteristics.

Applications

When used in plastisols, Plastomoll® DOA imparts low initial viscosity and good viscosity stability. The contribution to relative yield value suggests use in dip coating formulations where resistance to sag is required.

Safety

Plastomoll® DOA does not require special handling. Handle in accordance with good industrial hygiene and safety practices. Avoid eye contact by wearing personal protective equipment. If eye contact occurs, wash with flowing water and contact physician.

Avoid repeated or prolonged skin contact. Avoid breathing vapors by providing adequate ventilation.

Always refer to the Safety Data Sheet (SDS) for detailed information on safety.

Storage and Handling

Plastomoll® DOA can be stored for one year at temperatures below 40°C, if moisture is excluded.

Packaging

Plastomoll® DOA is available in bulk, tank trucks or rail cars.

Contact Information**Marketing**

BASF Corporation
11750 Katy Freeway, Suite 120
Houston, TX 77079, USA

Tel: +1 800-533-8961
Fax: +1 713-759-3036
E-mail: plasticizers@basf.com

Technical Support

BASF Corporation
4403 La Porte Highway 225
Pasadena, TX, 77501, USA

Tel: +1 281-884-4473 or -4432
Fax: +1 281-884-4302

Visit us online at

<http://www.plasticizers.basf.com>

Note

While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, it is provided for your guidance only. Because many factors may affect processing or application/use, we recommend that you make tests to determine the suitability of a product for your particular purpose prior to use. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF OUR TERMS AND CONDITIONS OF SALE. Further, you expressly understand and agree that the descriptions, designs, data and information furnished by BASF hereunder are provided gratis and BASF assumes no obligation or liability for the description, designs, data and information given or results obtained, all such being given and accepted at your risk.

© 2021 BASF Corporation