



1441 Branding Avenue, Suite 110
Downers Grove, IL 60515
PH: 800-353-7773
www.lpms-usa.com

TECHNICAL DATA SHEET

PRODUCT NAME: SPECTRA-MELT OMEGA PURGE 225

PRODUCT DESCRIPTION:

Thermoplastic hotmelt polyamide resin used for purging tanks, hoses and equipment to remove loose carbon particles (char) or when a resin color change is necessary.

The material is used for purge only and is not a reactive cleaner.

CHEMISTRY: POLYAMIDE

MARKET USE: PURGE MATERIAL

Product Property	TEST METHOD	Specification	Unit of Measure
Softening point	ASTM E 28	175-195	°C
Viscosity	ASTM D 3236 (RVT spindle 27)	225C 1500-4000	Centipoise
Color		amber	

RECOMMENDED USE TEMPERATURE: 225°C

HANDLING SUGGESTIONS: Before applying, it is necessary to read the Safety Data Sheet (SDS) for information about precautionary measures and recommendations. For chemical products exempt from compulsory labelling, the relevant precautions should always be observed.

The hot melt product should never be heated above the recommended use temperature. When the material is not being used, the temperature in the tank must be reduced to avoid oxidation and degradation of the material. The optimal standby temperature range for this material is 130°C for a maximum of 18 hours.

RESERVOIR CLEANING: Refer to LPMS-USA cleaning instructions



1441 Branding Avenue, Suite 110
Downers Grove, IL 60515
PH: 800-353-7773
www.lpms-usa.com

SAFETY PRECAUTIONS: No health hazards are expected when the hot melt is in the solid form. However, once melted, it can produce severe burns. The appropriate safety precautions should be used. If the molten adhesive makes contact with the operator's skin, cool the affected area immediately with cold water. Do not try to remove the adhesive from the skin, instead seek professional medical attention.

FORM OF SUPPLY: pellets

STORAGE: Keep in cool dry place in original closed container

The information above, particularly the recommendations for application and use of our products is based on our knowledge and experience. Due to the different substrates and conditions of application, which is beyond our knowledge and control, we strongly recommend carrying out sufficient tests to ensure that the product is suitable for the intended process and applications.

The data contained herein are furnished for information only and are believed to be reliable. LPMS-USA cannot assume responsibility obtained by others over whose methods we have no control. It is the user's responsibility to determine the suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, LPMS-USA specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose arising from sale or use of LPMS-USA products. LPMS-USA specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits. The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any LPMS-USA patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.