



Manufactured in semi-solid form for use as a combination cleaning, deoxidizing, protecting and lubricating preparation. Greases protect against oxidation (galvanic corrosion) and are free of mineral acids, sulphurs, alkalis and other noxious components aggressive to metals. DeoxIT® Greases improve performance of electrical contacts and mechanical components that require precise lubrication.

DeoxIT® Grease Type L260 - *Lithium-based preparation*.

Good lubrication, excellent wear resistance, excellent pressure resistance, excellent oxidation (galvanic corrosion) protection, high dripping-point characteristics.

Operating temperatures: L260: -40°C to 260°C.

NEW Unique DeoxIT® Grease Type L260D - Lithium-based preparation INFUSED WITH DeoxIT® D100L.

Select (#1) at: http://caig.com/technical-information/



Antenna connections, battery terminals, Buss bars, commutators, conductor rails, conductors, contactors, disconnects, drying & processing equipment, high amperage/high voltage applications, industrial electrical equipment (lifts, cranes, robotics, etc.), power tools, relays & switches (heavy duty, knife, step, rotary), etc.

USES - Mechanical:

Bearings (all types), doors (closures), drives (chain/sprockets), hatch closures, O-rings and seals, linear motion systems, plugs (threaded holes), rack & pinion assemblies, screw devices (jacks, rails), slide bushings, sliding parts, tracks/guides/rails, threaded closures, worm gears, etc.

DeoxIT® Products... used by those who demand the best!

Boeing General Electric McIntosh Labs Switchcraft Hewlett-Packard Motorola Daktronics **Tektronix** Diebold Inc. Honeywell Nokia **Union Pacific Dolby Laboratories** Intel Philips Healthcare Wayne-Dresser Rane Corp. Dover Elevator John Deere Xerox Corp. **Federal Express** Logitech Roland and many more!









GREASE TYPES:

DeoxIT® Type L260 Np, No particles
DeoxIT® Type L260 Cp, Copper particles
DeoxIT® Type L260 Ap, Aluminum particles
DeoxIT® Type L260 Qp, Quartz particles
DeoxIT® Type L260 Gp, Graphite particles
DeoxIT® Type L260 GQp, Graphite & Quartz
DeoxIT® Type L260 Tp, Teflon

GREASE DESCRIPTIONS:

No particles: Maximum lubrication for relatively clean surfaces.

Copper particles: Copper particles assist in breaking up oxidation and corrosion. Copper is conductive.

Aluminum particles: Use when aluminum metals are involved. Use in areas that two contacts will not touch and possibly short.

Quartz particles: Quartz particles assist in breaking up oxidation and corrosion. Quartz is nonconductive.

Graphite particles: Graphite particles assist in heat stability and lubrication. Graphite is excellent for heat transfer.

Graphite and Quartz particles: Use when heat transfer, lubrication and assistance is needed in breaking up oxides and corrosion.

Teflon: For superior lubrication and protection of parts.

Home of the DeoxIT® family of Environmentally-Safer Contact Cleaners and Connector Enhancing Treatments Made in USA























Audio/Video

Computers

Automotive Communications

Marine

Electrical

Energy

Photography

Security

Medical

Avionics

1. DeoxIT® Type L260Np, No particles, -40°C to 260°C

L260-N2G	2 gram Squeeze Tube
L260-N1	28 grams jar
L260-N8	226 grams jar
L260-N8TP	226 grams cartridge
L260-N35	35 lb. (16kg) pail

2. DeoxIT® Type L260Cp, Copper particles, -40°C to 260°C

L260-C1	28 grams jar
L260-C8	226 grams jar
L260-C8TP	226 grams cartridge
L260-C35	35 lb. (16kg) pail

3. DeoxIT® Type L260Ap, Aluminum particles, -40°C to 260°C

L260-A1	28 grams jar
L260-A8	226 grams jar
L260-A8TP	226 grams cartridge
L260-A35	35 lb. (16kg) pail

4. DeoxIT® Type L260Gp, Graphite particles, -40°C to 260°C

L260-G1	28 grams jar
L260-G8	226 grams jar
L260-G8TP	226 grams cartridge
L260-G35	35 lb. (16kg) pail

5. DeoxIT® Type L260Qp, Quartz particles, -40°C to 260°C

L260-Q1	28 grams jar
L260-Q8	226 grams jar
L260-Q8TP	226 grams cartridge
L260-Q35	35 lb. (16kg) pail

6. DeoxIT® Type L260GQp, Graphite/Quartz, -40°C to 260°C

L260-GQ1	28 grams jar
L260-GQ8	226 grams jar
L260-G8TP	226 grams cartridge
L260-GQ35	35 lb. (16kg) pail

7. DeoxIT® Type L260Tp, Teflon particles, -40°C to 260°C

L260-T1	28 grams jar
L260-T8	226 grams jar
L260-T8TP	226 grams cartridge
L260-T35	35 lb. (16kg) pail

COMPARISON CHART

Product	Heat Resistance	Wear Resistance	Water Resistance	Oxidation Resistance*	Oxidation Dissolving
DeoxIT® M260	Excellent	Very Good	Good	Very Good	Good
DeoxIT® L260	Very Good	Very Good	Very Good	Very Good	Good
DeoxIT® L260D	Excellent	Very Good	Excellent	Excellent	Very Good
Lithium	Good	Good	Good	Fair	Poor
Lithium Complex	Very Good	Good	Excellent	Fair	Poor
Complex	Very Good	Good	Excellent	Fair	Poor
Bentone Clay	Very Good	Very Good	Good	Good	Poor
Polyurea	Very Good	Good	Excellent	Good	Poor
Polyrex™	Excellent	Very Good	Good	Good	Poor

^{*} Oxidation of lubricants can produce sludge, varnish, gum and acid.

TYPICAL PROPERTIES (Base material):

•	TYPE:	L260
Flow Point, min.		-30°C
Viscosity @ 100°F, SUS		785
ASTM Dropping Point		260°C
Specific Gravity @ 20°C		1.85
Flash Point		300°C
¹ Lowest/Best Operating Tempera	ture (general)	-30°C
¹ Highest Operating Temperature	(continuous duty)	200°C
Acid & Neutralization No. (mg KOI	-l/g)	1.15
Saponification No. (mg KOH/g)		2.79
Electrical Conductivity (27°C)(10 ⁻¹	² ohm ⁻¹ cm ⁻¹)	0.17
² Dielectric Constant E _r		2.75
Tan ౮)(10⁴)		
² Dielectric Strength E _d (kV/cm)		54.6
² Insulation Resistance D (10 ⁻¹² oh	m-cm)	5.7
		+.50/03
Oil Type		Synthetic Blend
Soap Type		Lithium-12 Hydroxy
Soap %		9.52
ASTM - Penetration		295
NLGI		2
Deoxidizer		Yes
Oxidation Inhibitor		Yes
Corrosion Inhibitor		Yes
Texture		Short Fiber
Color		Amber

¹ Temperatures are conservative values for reference only.

All information and data contained in this literature is believed to be accurate, however, it should not be taken as definitive for all users. Users should thoroughly test advertised products in their application, and independently determine satisfactory results before use in large scale production or manufacturing processes. All information on the comparison chart on the front side of this literature we believe to be reliable and was, in part, provided by the manufacturer. Independent testing should be conducted to determine individual needs for each application.

VOC and RoHS Compliant

Product Information Sheet C-LM260, 7/2025



12200 Thatcher Court, Poway, CA 92064 U.S.A. **P:** 858/486-8388 **E:** info@caig.com **WEB:** www.caig.com | www.deoxit.com



[™] Polyrex is a trademark Of Exxon/Mobil Corporation

² **NOTE:** All values are relative to an ambient temperature of 26 to 28°C (approx. 80°F). Dielectric strength value is a statistical average taken from 10 measurings. Voltage measurement taken with 0.5% accuracy. Tests conducted on base material only. Greases with particles may have different measurements.